

Chemical / physical nature:

EP - 200 is a solvent free product based on epoxy, cured with amine hardener.

Mix ratio :

- 100 part resin
- 20 part hardener



Properties:

- Fast surface drying
- Fast curing at low temperatures
- Usable in furnace curing processes

Storage:

EP - 200 should be storage indoors in original Unopened and undamaged containers in a dry place at storage temperature under 25 °C. Exposure to sunlight should be avoided.

Stability:

Under the above mentioned storage condition the stability of EP - 200 will be 9 month ex work

Technical information:

Specific	Amount	Unit	Standard
Appearance	Viscos liquid		
Color	Light yellow		
Solid content	100	Percent	ASTM D3251
Gel time	15	Min	Internal standard
Viscosity	1000 - 3000	CPS	ISO 2555

*100 gr mixture of resin and hardener at 25 °C