

### Chemical / physical nature:

Polytox EP - 96 is an epoxy based on BPHA with polyamine.

This resin intended for reinforced marble stone with fast curing.

### Mix ratio:

- 100 part resin
- 20 part hardener



### Properties:

- Fast surface drying
- Light color
- Fast curing
- Good adhesive to stone
- Good permeability

### Storage:

EP - 96 should be storage indoors in original Unopened and undamaged containers in a dry place at storage temperature under 25 °C. Exposure to sunlight should be avoided.

### Stability:

Under the above mentioned storage condition the stability of EP - 96 will be 9 month ex work

### Technical information:

Specific	Amount	Unit	Standard
Appearance	Viscos liquid		
Color	Less than 1		
Percent Solid	96 - 98	Gardener	ISO 3251
Color	10	Percent	ASTM D1544
Gel time	40 - 55	Min	Internal standard
Viscosity	350 - 550	CPS	ISO 2555