

**WOOD PAINT – FAST RED CELLULOSE PUTTY (P757R)****Product description:**

Nitrocellulose putty based on nitrocellulose with excellent filling and sanding properties prepares the wood surface for subsequent coatings.

Application:

This coating is used to protect wood in different weather conditions. The outstanding features of this coating can be called excellent adhesion to the surface, hardness, resistance to wear (sanding).

Technical data:

Specification	Details	EN Standard	ASTM Standard
Color / Shade	Red	EN ISO 11664	D2244
Solid by Volume %	70 ± 5%	EN ISO 3233-1 / 3233-2	D2697
Solid by weight %	90 ± 5%	EN ISO 3251	D2369
Specific Gravity (Density) g/cm ³	1.3 - 1.5 gr/cm ³	EN ISO 2811	D1475
Shelf life	12 months		
Dry Film Thickness (DFT) μm	80 - 90 μ	EN ISO 2808	D7091
Wet Film Thickness (WFT) μm	110 -120 μ	EN ISO 2808	D4414
Theoretical coverage strength m ² /L	7 - 9 m ² /lit	EN ISO 6504	Calculated
Flash point	30 °C	EN ISO	D
Hardening mechanism	Solvent evaporation		
Touch Dry	5 - 10 Min	EN ISO 9117-3	D1640
Through Dry (Deep Drying)	1 hours	EN ISO 9117-1	D1640
Hardness / Final Cure	24 hours	EN ISO 15184	D3363

The drying time depends on the film thickness applied, all the data in this catalog are based on the thickness of the dry film in vitro conditions.

Equipment Used:

The coating is applied on the surface of the wood by means of a smooth.

Environmental Conditions:

The desired surface should be clean, dry and free from any contamination.

Surface Preparation:

Before applying the above coating, dust and moisture must be removed from the surface because moisture and water cause peeling and lack of proper adhesion of the coating to the surface.

Method of Applying:

All equipment should be cleaned with recommended thinner before use.

Safety Tips:

This coating is flammable and should be kept away from flame and heat, and the executor is also obliged to study and observe the MSDS conditions of this product, to wear special masks and safety gloves when using and in environments with proper ventilation.

Storage Conditions:

It should be kept in a closed space and away from direct rays at a temperature of 35 - 50 C⁰. In addition, the storage time of the product is five years.

Considerations:

The drying time depends on the film thickness applied, all the data in this catalog are based on the thickness of the dry film in vitro conditions.



LEGAL NOTES : : The information contained in this Technical Data Sheet is based on laboratory testing and practical experience. Actual performance may vary depending on substrate condition, application method, and environmental conditions. Users should test suitability before large-scale application.

Head Office : Building No.15 , Qasimlu Street 40, Shahidan Zargata Quarter 24, Zone 1, Sulaymaniyah 46001, Iraq

Factory : Tanjaro Industrial Area – Sulaymaniyah – Iraq