

## PROPERTIES:

AC- 466 is an acrylic resin with hydroxyl(OH) group which reacts with isocyanate and melamine formaldehyde compounds.

## Application:

This product is recommended for production of two component poly urethane coatings with excellent resistance against chemicals and weather conditions



## Specific characteristics:

- High brightness
- Resistance against weather conditions
- Excellent adherence to the surface

## Storage:

Keep away from direct sunlight and under 25°C.

## Stability:

Under aforementioned conditions: 12 months from production date.

## Technical information:

Characteristics	Rang/Value	Unit	Ref.Standard
Solvent	Xylene		
Appearance	Viscose liquid	---	---
Color	Less than 1	Gardner	---
OH content	2.8%		
Percent solids	60 ± 2	%	ISO 3251
Viscosity	7000-90000	CP	ISO 2555
Acid Value	Max: 20	mg KOH/g	ISO 2144