



Product description:

This coating is based on alkyd resin and contains micronized powders and iron oxide pigment, which will increase the color's resistance against corrosion and humidity. This coating has excellent hardness and adhesion for metal structures located in moderate weather conditions.

Application:

This product with unique compounds is used on all metal surfaces, especially iron, and protects these surfaces from rust.

Technical data:

Specification	Details	EN Standard	ASTM Standard
Solid by Volume (%)	up to 65%	EN ISO 3233	D2697
Viscosity	5 - 105 KU	EN ISO 2431, 32198	D2196/ D1200 / D5125 (2025)
Density / Specific gravity g/cm3	1.6 gr/cm3 KU	EN ISO 2811	D1475 (2025)
Adhesion	B4	EN ISO 2409 / 4624	D3359 (Cross-cut) / D4541 (Pull-off)
Surface Drying / Touch Dry	45 min	EN ISO 9117-1	D1640
deep drying time (Through Dry)	3 hours	EN ISO 9117-3	D1640
Covering at least / Hiding Power	20-25 m2	EN ISO 6504	D2805
Water Resistance (Cold Water)	24 hours	EN ISO 2812-2	D870
Flexibility Bending	1500 gr	EN ISO 1519	D522 (Mandrel Bend)
Moisture resistance	24 hours	EN ISO 6270	D2247 (Humidity Cabinet)
Can be used with / Compatibility	brush, sprayer, roller the resulting crust should be uniform	EN ISO 1524	D2243
Resistance to petroleum solvents	2 hours Be resistant to the closing procedure (do not have a procedure) Color stability in stock to match the smell matches	EN ISO 2812-1	D1308

FURNACE PAINTS- OCHER STAINLESS-STEEL CLUSTER (1195)

Equipment Used:

Various types of rollers, pistols and brushes are suitable for performing this coating.

Environmental Conditions:

This product can be run at 5 - 35°C on dry place.

Surface Preparation:

The surface should be clean, dry and free from any contamination. Fresh gypsum surfaces usually do not require preparation, but old and old surfaces should be primed.

Method of Applying:

- You can hit the surface if needed.
- Then the item product Dilute the solution with suitable thinner and apply with suitable equipment be made.

Safety Tips:

This product is water-based and not flammable. However, it is recommended that in case of contact with the skin, wash it with soap and large amounts of water, and in case of further skin sensitivity and irritation, see a doctor.

Storage Conditions:

This product should be in a closed space and away from direct rays .The temperature should be kept at 5 - 35 degrees .

Considerations:

The available information is based on our technical knowledge and laboratory research, but since the conditions and methods of application are different and out of reach, we do not guarantee the results of it.



LEGAL NOTES : The information contained in this Technical Data Sheet is based on laboratory testing and practical experience. Actual performance may vary depending on substrate condition, application method, and environmental conditions. Users should test suitability before large-scale application.

Head Office : Building No.15 , Qasimlu Street 40, Shahidan Zargata Quarter 24, Zone 1, Sulaymaniyah 46001, Iraq

Factory : Tanjaro Industrial Area – Sulaymaniyah – Iraq